

SAM™ data sheet SAM-1040-28-3ps-x, $\lambda = 1040$ nm

Laser wavelength	$\lambda = 1040$ nm
Absorbance	$A_0 = 28$ %
Modulation depth	$\Delta R = 20$ %
Non-saturable loss	$A_{ns} = 8$ %
Saturation fluence	$\Phi_{sat} = 40$ $\mu\text{J}/\text{cm}^2$
Relaxation time constant	$\tau \sim 3$ ps
Damage threshold	$\Phi = 2$ mJ/cm^2
Chip area	4.0 mm x 4.0 mm; other dimensions on request
Chip thickness	450 μm

Mounting option **x** denotes the type of mounting as follows:

x = 0	unmounted
x = 12.7 g	glued on a copper heat sink with 12.7 mm \varnothing
x = 25.4 g	glued on a copper heat sink with 25.4 mm \varnothing
x = 12.7 s	soldered on a copper heat sink with 12.7 mm \varnothing
x = 25.4 s	soldered on a copper heat sink with 25.4 mm \varnothing
x = 25.4 w	soldered on a water cooled copper heat sink with 25.4 mm \varnothing
x = FC	mounted on a 1 m single mode fiber cable with FC connector

Low intensity spectral reflectance

