

SOC data sheet SOC-1040-6-0.5-1ps-x, λ = 1040 nm

Laser wavelength	$\lambda = 1040 \text{ nm}$
Absorptance	$A_0 = 6 \%$
Transmittance	T = 0.5%
Refelctance	R = 93 %
Modulation depth	$\Delta R = 3.5 \%$
Non-saturable loss	$A_{ns} = 1.5 \%$
Saturation fluence	Φ_{sat} = 70 μ J/cm ²

Relaxation time constant $\tau \sim 1 \text{ ps}$

Chip area 5.0 mm x 5.0 mm; other dimensions on request

Chip thickness 625 µm; semi-insulating GaAs


Front side protection with a dielectric layer

Back side AR coating the SOC back side is polished and antireflection coated for 1064 nm

Mounting option \mathbf{x} denotes the type of mounting as follows:

$\mathbf{x} = 0$	unmounted
x = 12.7 g	glued on a gilded Cu-cylinder with 12.7 mm \varnothing and 4 mm \varnothing center hole
x = 25.0 g	glued on a gilded Cu-cylinder with 25. mm \varnothing and 4 mm \varnothing center hole
x = 25.4 g	glued on a gilded Cu-cylinder with 25.4 mm \varnothing and 4 mm \varnothing center hole
x = FC	mounted on a 1 m single mode fiber cable with FC connector

Spectral reflectance and transmittance





Spectral reflectance and transmittance

